

Orientační převodní tabulka (z původních ČSN) norem tvářené mědi a Cu slitin

ČSN	ozn. ČSN	ozn. DIN	Wr.Nr.	ozn. EN	Wr.EN
Měď tvářená					
423000	Cu 99,95	OF-Cu	2,0040	Cu-OF	CW008A
423001	Cu 99,9E	E-Cu 58 E-Cu 57	2,0060	Cu-ETP	CW004A
423002	Cu 99,95	-	-	-	-
423003	Cu 99,85 (CuP)	SF-Cu	2,0090	Cu-DHP	CW024A
423004	Cu 99,75	-	-	-	-
423005	Cu 99,5	-	-	-	-
423209	Cu 99,2 As	-	-	-	-
Slitiny mědi tvářené					
423010	E CuSn	-	-	-	-
423013	CuSn4	CuSn4	2.1016	CuSn4	CW450K
423016	CuSn6	CuSn6	2.1020	CuSn6	CW452K
423018	CuSn8	CuSn8	2.1030	CuSn8	CW453K
ISO 427	CuSn8P	-	-	CuSn8P	CW459K
423019	CuCd 0,2	-	-	-	-
423042	CuAl5	CuAl5As	2.0918	CuAl5As	CW300G
423044	CuAl9Mn2	CuAl9Mn2	2.0960	-	-
423045	CuAl9Fe3	CuAl8Fe3	2.0932	CuAl8Fe3	CW303G
423046	CuAl10Fe3Mn1,5	CuAl10Fe3Mn2	2.0936	CuAl10Fe3Mn2	CW306G
423047	CuAl10Fe4Ni4	CuAl10Ni5Fe4	2.0966	CuAl10Ni5Fe4	CW307G
423048	CuAl9Ni5Fe1Mn1	-	-	-	-
423053	CuSi3Mn	CuSi3Mn	2.1525	CuSi3Mn	CW116C
423054	CuNi2Si	CuNi2Si	2.0855	CuNi2Si	CW111C
423056	CuMn13Ni	-	-	-	-
423058	CuCd1	CuCd1	2.1266	CuCd1,0	CW131C
423063	CuNi30FeMn	CuNi30Mn1Fe	2.0882	CuNi30Mn1Fe	CW354H
423064	CuNi30Mn2 (nikelin)	CuNi30Mn	2.0890	-	-
423065	CuNi45Mn2 (konstantan)	CuNi44Mn1	-	-	-
423200	CuZn4	-	-	-	-
ISO 426-1	CuZn5	CuZn5	2.0220	CuZn5	CW500L
423201	CuZn10	CuZn10	2.0230	CuZn10	CW501L
423202	CuZn15	CuZn15	2.0240	CuZn15	CW502L
423203	CuZn20	CuZn20	2.0250	CuZn20	CW503L
423210	CuZn30	CuZn30	2.0265	CuZn30	CW505L
423212	CuZn32	CuZn33	2.0280	CuZn33	CW506L
423213	CuZn37	CuZn37	2.0321	CuZn37	CW508L
-	-	CuZn36	2.0335	CuZn36	CW507L
423214	CuZn36Pb1	CuZn36Pb1,5	2.0331	CuZn35Pb2	CW601N
423220	CuZn40	CuZn40	2.0360	CuZn40	CW509L
423221	CuZn38Pb	CuZn39Pb0,5	2.0372	CuZn39Pb0,5	CW610N
423222	CuZn39Pb1	-	-	CuZn39Pb1	CW611N
423223	CuZn40Pb2	CuZn40Pb2	2.0402	CuZn40Pb2	CW617N
-	-	CuZn39Pb2	2.0380	CuZn39Pb2	CW612N
-	-	CuZn36Pb3	2.0375	CuZn36Pb3	CW603N
ISO 426-2	CuZn38Pb2	CuZn38Pb1,5	2.0371	CuZn38Pb2	CW608N
ISO 426-2	CuZn39Pb3	CuZn39Pb3	2.0401	CuZn39Pb3	CW614N
423226	CuZn45Pb3Mn3Fe	-	-	-	-

INKOSAS a.s., Antala Staška 1859/34, CZ-140 00 Praha 4

Tel.: +420 246052543, Fax: +420 246052545

E-mail: inkosas@inkosas.cz, Web: www.inkosas.cz

Slitiny mědi tvářené - pokračování					
423231	CuZn40Mn3Al1	-	-	-	-
423234	CuZn40Mn	CuZn40Mn2	2.0572	CuZn40Mn2Fe1	CW723R
423237	CuZn38Sn1	CuZn38Sn1	2.0530	CuZn38Sn1As	CW717R
423238	CuZn38SnMnAs	-	-	-	-
423239	CuZn28AlSnMn	-	-	(CuZn28Sn1As)	CW706R
423256	CuNi15Zn21	CuNi12Zn24	-	CuNi12Zn24	CW403J